



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>5</sup> : C08K 13/04, C08L 67/02 // (C08K 13/04, 3:02, 5:3492 C08K 7:14)</p>	<p><b>A1</b></p>	<p>(11) International Publication Number: <b>WO 92/09653</b> (43) International Publication Date: 11 June 1992 (11.06.92)</p>
<p>(21) International Application Number: PCT/GB91/02078 (22) International Filing Date: 25 November 1991 (25.11.91) (30) Priority data: 9025727.0 27 November 1990 (27.11.90) GB (71) Applicant (for all designated States except US): BIP CHEMICALS LIMITED [GB/GB]; 20 St. Mary's Parsonage, Manchester M3 2NL (GB). (72) Inventor; and (75) Inventor/Applicant (for US only) : WILLIAMS, Richard, Stuart [GB/GB]; 16 Browning Road, Rugby, Warwickshire CV21 4BT (GB). (74) Agents: CRUX, John, Anthony et al.; T&amp;N plc, Bowdon House, Ashburton Road West, Trafford Park, Manchester M17 1RA (GB).</p>		<p>(81) Designated States: AT (European patent), BE (European patent), CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (European patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent), US.</p> <p><b>Published</b> <i>With international search report.</i> <i>With amended claims.</i></p>
<p>(54) Title: IMPROVEMENT IN OR RELATING TO POLYESTER COMPOSITIONS</p>		
<p>(57) Abstract</p> <p>A moulding composition which consists of a saturated polyester such as polyethylene terephthalate or polybutylene together with reinforcing fibres and, as fire retardant system, red phosphorus with melamine cyanurate.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU <sup>+</sup>	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE*	Germany	MC	Monaco	US	United States of America
DK	Denmark				

+ Any designation of "SU" has effect in the Russian Federation. It is not yet known whether any such designation has effect in other States of the former Soviet Union.

- 1 -

Improvements in or relating to polyester compositions

This invention relates to polyester compositions, and particularly to those based on thermoplastic polyesters such as polyethylene terephthalate (PET) and polybutylene terephthalate.

Thermoplastic polyesters are commonly used in moulding compositions, and when flame retardant grades are required they are typically flame retarded with additives containing halogens. The level of flame retardancy obtained from such materials can be very good and V0 ratings in the Underwriters (UL) Flammability test are readily achieved. A problem with such compositions, however, is that the resistance to electrical tracking of thermoplastic polyesters containing these additives is very low. (Typical values of Comparative Tracking Index - CTI - for a UL V0 material would be around 200 volts.)

It has also been proposed to use red phosphorus as a flame retardant in PET and PBT compositions, whereby some improvement in electrical tracking resistance may be achieved.

US Patent No 4,314,927 proposes the use of red phosphorus and melamine cyanurate in moulding compositions of Nylon 66 to improve the heat stability and lower the level of phosphorus required to achieve V0 ratings. It gives no guidance as to the electrical tracking resistance of the compounds disclosed.

We have now found that red phosphorus and melamine cyanurate may be used together in glass reinforced thermoplastic polyester compositions to enhance both flame retardancy and electrical tracking resistance.

Thus according to the present invention a polyester moulding composition comprises a thermoplastic polyester, reinforcing fibres and as fire retardant red phosphorus with melamine cyanurate.

The thermoplastic polyester may be, for example, polyethylene terephthalate (PET) or polybutylene terephthalate (PBT) or a polyester containing at least 80 per cent by weight of repeating units derived from ethylene terephthalate or butylene terephthalate.

The amount of thermoplastic polyester in the composition is preferably in the range 35 to 75 per cent by weight of the total composition.

As flame retardant red phosphorus is an essential ingredient of the polyester moulding composition but the red phosphorus is preferably treated in order to reduce its handling difficulties, since red phosphorus alone can be very dangerous in handling. Thus the red phosphorus may be carried on a polymeric carrier, and/or may be encapsulated with a suitable substance such as a polymer or resin.

Preferably the amount of red phosphorus in the composition is 1 to 15 per cent by weight of the total composition.

The composition contains reinforcing fibres, for example short lengths of inorganic reinforcing fibre such as glass fibre, although other types of fibre which will stand up to the processing conditions to which the composition is subjected may be used. The amount of reinforcing fibre in the composition is preferably in the range 15 per cent to 45 per cent by weight of the composition.

Fillers may also be used in the composition, for example kaolinitic clays, talc, glass spheres, wollastonite, calcium carbonate, and when used in conjunction with the

reinforcing fibres have the advantage of giving a composition with less warping and less anisotropic properties.

The composition may also contain a nucleant and the nucleant may be either a metal salt of an organic acid, for example a metal stearate, acetate or benzoate, or a finely divided material which does not melt at or below the melting point of polyethylene terephthalate, for example microtalc. The preferred nucleant is a group 1 metal stearate, or microtalc with a particle size of less than 20 microns.

Preferably the group 1 metal stearate is sodium stearate, which is a known nucleant for polyethylene terephthalate and gives easier nucleation of the polyester. The nucleant is preferably used in an amount no more than 1% by weight of the composition, particularly in the range 0.1 to 0.7 per cent by weight. However, if a finely divided solid nucleant is used it may be used in greater proportion, eg up to six parts by weight per 100 parts by weight total polymer, and may be used, if desired, in addition to a nucleant of the other type.

In the compositions of this invention the melamine cyanurate functions to enhance the flame retardancy of the system with an important improvement in the electrical

tracking resistance of the moulded composition. The amount of melamine cyanurate used may be in the range from 1 per cent to 20 per cent, preferably 4 per cent to 15 per cent, by weight of the composition.

Other additives such as mould release agents, stabilisers etc may be used in the composition as desired.

The invention will now be described in more detail, by way of example only, by means of the following Examples.

## EXAMPLES

### Flammability Testing

The method used was the standard Underwriters Laboratories test method UL94. V0 means that the specimens burnt for less than 10s after removal of flame, that the total burn time for ten applications of the flame on five specimens was less than 50 seconds. In addition no flaming drops are permitted. In V1 classification no specimen burns for longer than 30 seconds after the application of the flame and the total burning time for 10 specimens is less than 250 seconds. No flaming drops are permitted. The same criteria apply in V2 classification except that some flaming drops are permitted.

In addition to these classifications, the average burning time for each application of flame was calculated and the occurrence of non-flaming drops was noted (10 specimens).

#### Electrical Tracking Resistance Testing

The test equipment used is that of the Comparative Tracking Index test of the European Standard IEC 112 (DIN 53480). An aqueous solution containing 0.1%  $\text{NH}_4\text{Cl}$  was dropped at 30 second intervals on to the surface of the mouldings between two electrodes carrying the applied voltage. Platinum electrodes were used, with trips at 0.5 amps and 2 secs.

Results are expressed in the tables below for each applied voltage as "failures", or "passes" at 50 drops total.

#### Examples 1 and 2

Two compositions of polyethylene terephthalate (PET) were prepared with and without melamine cyanurate for comparison.

The compositions were made by first blending the ingredients shown (as parts by weight) in Table I, and then fully compounded in a Baker Perkins twin-screw extruder.

TABLE I

<u>Ingredient</u>	<u>Example 1</u>	<u>Example 2</u>
PET (D217)	60	50
Coated Red Phosphorus	7.2	7.2
Glass Fibre	30	30
Nucleant/Mould Release Agent	3	3
Melamine Cyanurate "C"	0	10
Stabiliser	0.25	0.25

In each example the red phosphorus used (MASTERFLAM P70S) was encapsulated in a polyamide carrier (70% by weight of red phosphorus). The glass fibres were grade 429YZ from Owens Corning Fibreglass, chop length 4.5mm. The nucleant/mould release agent was NAI/LOXIOL masterbatch and the stabiliser was IRGAFOS PEPQ. NAI is a nucleant/polymer (linear low density polythene) supplied by Goodyear. LOXIOL is pentaerythritol tetrastearate supplied by Henkel.

Sample mouldings were made by injection moulding from each composition on a standard BIPEL 60/26 machine using a barrel temperature of 270°C.

These were tested for flammability and for Electrical Tracking Resistance. The results of these tests are given below in Table II.

TABLE II

<u>Test</u>	<u>Example 1</u>	<u>Example 2</u>
Flammability - UL94 test		
a) At 1.5mm		
Class	V0	V0
Average Burn Time (secs)	0.7	0
b) At 3mm		
Class	V0	V0
Average Burn Times (secs)	0.1	0
Electrical Tracking Resistance		
At 400V	Fail	Pass
	(at 6 and 18 drops)	(5 passes at >52 drops)

Examples 3 and 4

Two compositions of polybutylene terephthalate (PBT) were prepared with and without melamine cyanurate for comparison.

The compositions were made by first blending the ingredients shown (as parts by weight) in Table III, and then fully compounded in a Baker Perkins twin-screw extruder.

TABLE III

<u>Ingredient</u>	<u>Example 3</u>	<u>Example 4</u>
PBT (TQ9)	60	50
Coated Red Phosphorus	7.2	7.2
Glass Fibre	30	30
Nucleant/Mould Release Agent	3	3
Melamine Cyanurate "C"	0	10
Stabiliser	0.25	0.25

In each example the red phosphorus used (MASTERFLAM P70S) was encapsulated in a polyamide carrier (70% by weight of red phosphorus). The glass fibres were grade 429YZ from Owens Corning Fibreglass, chop length 4.5mm. The nucleant/mould release agent was NAI/LOXIOL masterbatch and the stabiliser was IRGAFOS PEPQ. NAI is a nucleant/polymer (linear low density polythene) supplied by Goodyear. LOXIOL is pentaerythritol tetrastearate supplied by Henkel. Sample mouldings were made by injection moulding from each composition on a standard BIPEL 60/26 machine using a barrel temperature of 270°C.

These were tested for flammability and for Electrical Tracking Resistance exactly as for Examples 1 and 2. The test results were very similar; Example 3 failed and Example 2 passed.

CLAIMS

1. A polyester moulding composition which comprises thermoplastic polyester, reinforcing fibres and as fire retardant red phosphorus with melamine cyanurate.
2. A moulding composition according to claim 1 in which the thermoplastic polyester is polyethylene terephthalate or polybutylene terephthalate or polyester containing at least 80 per cent by weight of repeating units derived from ethylene terephthalate or butylene terephthalate.
3. A moulding composition according to claim 1 or 2 in which the amount of the thermoplastic in the composition is in the range 35-75 per cent by weight of the total composition.
4. A moulding composition according to any preceding claim in which the amount of red phosphorus in the composition is in the range 1-15 per cent by weight of the total composition.

5. A moulding composition according to any preceding claim in which the amount of reinforcing fibres is in the range 15-45 per cent by weight of the total composition.
6. A moulding composition according to claim 5 in which the reinforcing fibres are inorganic reinforcing fibres such as glass fibres.
7. A moulding composition according to any preceding claim which additionally comprises at least one filler.
8. A moulding composition according to any preceding claim which also contains a nucleant for the thermoplastic polyester.
9. A moulding composition according to claim 8 in which the nucleant is a Group 1 metal stearate, or micro talc with a particle size of less than 20 microns.
10. A moulding composition according to any preceding claim in which the amount of melamine cyanurate is in the range from 1-20 per cent by weight of the total composition.

11. A moulding composition according to claim 10 in which the amount of melamine cyanurate is in the range 4-15 per cent by weight of the total composition.
  
12. A moulding composition substantially as described herein in the foregoing Example 2.

**AMENDED CLAIMS**

[received by the International Bureau  
on 23 April 1992 (23.04.92);  
original claims 1 and 2 replaced by amended claim 1; remaining claims  
unchanged but renumbered as claims 2-11 (3 pages)]

1. A polyester moulding composition comprising thermoplastic polyester constituted by polyethylene terephthalate, or polybutylene terephthalate or polyester containing at least 80 per cent by weight of repeating units derived from ethylene terephthalate or butylene terephthalate, reinforcing fibres and as fire retardant red phosphorus with melamine cyanurate.
2. A moulding composition according to claim 1 in which the amount of the thermoplastic in the composition is in the range 35-75 per cent by weight of the total composition.
3. A moulding composition according to claim 1 or claim 2 in which the amount of red phosphorus in the composition is in the range 1-15 per cent by weight of the total composition.


4. A moulding composition according to any preceding claim in which the amount of reinforcing fibres is in the range 15-45 per cent by weight of the total composition.
5. A moulding composition according to claim 4 in which the reinforcing fibres are inorganic reinforcing fibres such as glass fibres.
6. A moulding composition according to any preceding claim which additionally comprises at least one filler.
7. A moulding composition according to any preceding claim which also contains a nucleant for the thermoplastic polyester.
8. A moulding composition according to claim 7 in which the nucleant is a Group 1 metal stearate, or micro talc with a particle size of less than 20 microns.
9. A moulding composition according to any preceding claim in which the amount of melamine cyanurate is in the range from 1-20 per cent by weight of the total composition.

10. A moulding composition according to claim 9 in which the amount of melamine cyanurate is in the range 4-15 per cent by weight of the total composition.
  
11. A moulding composition substantially as described herein in the foregoing Example 2.

## INTERNATIONAL SEARCH REPORT

PCT/GB 91/02078

International Application No

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) <sup>6</sup>		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 C08K13/04; C08L67/02; //(C08K13/04, 3:02, 5:3492, 7:14)		
<b>II. FIELDS SEARCHED</b>		
Minimum Documentation Searched <sup>7</sup>		
Classification System	Classification Symbols	
Int.Cl. 5	C08K ; C08L	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched <sup>8</sup>		
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b>		
Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
Y	DE,A,2 126 923 (FARBWERKE HOECHST AG) 30 November 1972 see claims ---	1-12
Y	US,A,4 180 496 (AKIRA YANAGIMOTO ET AL.) 25 December 1979 see claims ---	1-12
Y	EP,A,0 019 768 (BASF AKTIENGESELLSCHAFT) 10 December 1980 cited in the application see the whole document ---	1
<p><sup>10</sup> Special categories of cited documents :</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&amp;" document member of the same patent family</p>		
<b>IV. CERTIFICATION</b>		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
04 MARCH 1992	17 MAR 1992	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	P. Los Arcos E. 	

**ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO. GB 9102078  
SA 53505**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 04/03/92

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE-A-2126923	30-11-72	AT-B- 324003	11-08-75
		AU-B- 465361	25-09-75
		AU-A- 4278772	29-11-73
		BE-A- 784125	29-11-72
		CA-A- 987041	06-04-76
		CH-A- 569046	14-11-75
		FR-A- 2140043	12-01-73
		GB-A- 1358351	03-07-74
		NL-A- 7206975	01-12-72
US-A-4180496	25-12-79	JP-C- 1307140	13-03-86
		JP-A- 53088854	04-08-78
		JP-B- 60033850	05-08-85
EP-A-0019768	10-12-80	JP-C- 1428982	09-03-88
		JP-A- 55161848	16-12-80
		JP-B- 62034268	25-07-87
		US-A- 4314927	09-02-82